

TEST REPORT

No. : SHIN1512055408MR

Date : Dec 08, 2015

Page: 3 of 3

Test Item: Dimensional Stability

Sample Description: Transparent plastic film

Test Method: ASTM D1204-14 and client's requirement

Test Condition:

Specimen: 250mm×250mm

Test condition: 23 ± 2 °C, 50 ± 5 % RH, 25 h—23 ± 2 °C, 50 ± 5 % RH, 1 h

Medium: Talc powder

Lab Environmental Condition: 23 ± 2 °C, 50 ± 5 % RH

Test Result:

Test Item	Test Result	
Dimensional Stability	Length	-0.1 %

Note:

1. Dimensional Stability, %=(Dimension after test-Dimension before test)/Dimension before test× 100
2. Test specimens were cut from the sample.

Original sample Photo:



***** End of report *****



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/terms-and-conditions.aspx> and, for electronic forest documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/terms-and-conditions/terms-and-conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction clauses defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings of the facts of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing/inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Dispatch@sgs.com
 1155 East Kang Qiao Road, Pudong District, Shanghai, China 201319 1 (86-21) 61196300 1 (86-21) 68183122/88183200 www.sgs.com.cn
 中国·上海·浦东康桥东路1155号 60号 邮编: 201319 1 (86-21) 61196300 1 (86-21) 68183122/88183200 e.sgs.china@sgs.com